

## Declaration of Performance

No. 001DoP-CDC-B1a

- 1: **Unique identification code of the product type** : Dry-Pressed ceramic tiles, with water absorption  $E_b \leq 0,5\%$ .
- 2: **Intended use** : For internal and external walls and floorings.
- 3: **Name or registered trade mark, and contact address of the manufacturer** : Ceramica del Conca S.p.a. - Via Croce, 8 – 47832 San Clemente (RN) - Italia
- 4: **System of assessment and verification of constancy of performance (AVCP)** : 4
- 5: **Name and identification number of notified laboratory, if relevant**: not applicable
- 6: **Declared performance**:

<u>Essential Characteristics</u>	<u>Performance</u>	<u>Harmonized Technical Specification</u>
Reaction to fire	A1 - A1 <sub>FL</sub>	EN 14411:2012
Release of dangerous substance, for		
Cadmium	NPD	
Lead	NPD	
Breaking Strength:	> 1300 N	
Slipperiness	See table attached	
Tactility	NPD	
Bond strength/adhesion for:		
Cementitious adhesive, type C2	1 N/mm <sup>2</sup>	
Thermal shock resistance	Pass	
Durability		
Internal use:	Pass	
External use: (freeze-thaw resistance)	Pass	

The performance of the product identified in point 1 is in conformity with the declared performance in point 6.  
This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 3.

Signed for and on behalf of the manufacturer by: Luca Costi Technical Director

Place and date of issue

San Clemente, 02/08/17

Signature

  
**CERAMICA DEL CONCA SpA**  
 47832 - SAN CLEMENTE (RN) Italy  
 Fraz. Sant'Andrea in Casale  
 Cod. Fisc. e P. IVA: 00819720400  
 Tel. 0541-988453 - Fax 0541-988783

This document of performance does not include decorative accessories, trim and mosaic.

		DIN51130	DIN51097	ANSI 137.1 (DCOF)		BCRA		
				bagnato/wet	asciutto dry	bagnato/wet		
Porcellana d'arredo	HZG - Zelo Grip	R13	C	≥0,42	>0,40	>0,40		
	KY	R9		≥0,42	>0,40	>0,40		
	O		A					
Rover	TE - Terminus	R9*	B*	≥0,42*	>0,40*	>0,40*		
	AR - Artelegno	R9*	B*	≥0,42*	>0,40*	>0,40*		
	DL - Dolomiti	R10	B	≥0,42	>0,40	>0,40		
	DG - Dolomiti Grip	R12	C	≥0,42	>0,40	>0,40		
	DV - Da Vinci	R10	B	≥0,42	>0,40	>0,40		
	EK - Epokal	R9*	B*	≥0,42*	>0,40*	>0,40*		
	LB - Bosco di Casole	R9	B	≥0,42	>0,40	>0,40		
	LF - In Out	R10	B	≥0,42		>0,40		
	LG - In Out Grip	R12	C	≥0,42	>0,40	>0,40		
	LM - Montenapoleone	R9	B	≥0,42	>0,40	>0,40		
	FI - Foreste d'Italia	R9	B	≥0,42	>0,40	>0,40		
	FG - Foreste d'Italia Grip	R12	C	≥0,42	>0,40	>0,40		
	GP - Gran Paradiso	R9	B	≥0,42	>0,40	>0,40		
	MN - Monteverde	R9	B	≥0,42	>0,40	>0,40		
	MG - Monteverde Grip	R12	C	≥0,42	>0,40	>0,40		
	SA - Saloon	R9	B	≥0,42	>0,40	>0,40		
	Fast	LM FAST	R9	B	≥0,42	>0,40	>0,40	
HFO FAST		R9	A	≥0,42	>0,40	>0,40		
SA FAST		R9	B	≥0,42	>0,40	>0,40		
HAL - Halo		R9	B	≥0,42	>0,40	>0,40		
Hard	HBQ - Blue Quarry	R9	B	≥0,42	>0,40	>0,40		
	HCL - Climb	R10	B	≥0,42	>0,40	>0,40		
	HCL - Climb grip	R12	C	≥0,42	>0,40	>0,40		
	HCP - Les Baux de Provence	R11	A	≥0,42	>0,40	>0,40		
	HDG - Dogma	R9*	B*	≥0,42*	>0,40*	>0,40*		
	HDT - Docet	R9*	B*	≥0,42*	>0,40*	>0,40*		
	HEG - Engadina	R9	B	≥0,42	>0,40	>0,40		
	HGA - GA by Giugiaro	R9	B	≥0,42	>0,40	>0,40		
	HGT - Galestro	R11	C	≥0,42	>0,40	>0,40		
	HMC - Mulini di Canepa	R11	B	≥0,42	>0,40	>0,40		
	HNT - Nat	R12	B	≥0,42	>0,40	>0,40		
	HPE - Hyper	R11	C	≥0,42	>0,40	>0,40		
	HPR - Pietra Regia	R11	C	≥0,42	>0,40	>0,40		
	HRC	R10		≥0,42	>0,40	>0,40		
	HRK - Rustiko	R12	C	≥0,42	>0,40	>0,40		
	HRI - Rock Island	R11	B	≥0,42	>0,40	>0,40		
	HRN - Carpegna	R9		≥0,42	>0,40	>0,40		
	HRT - Rockstar	R12	C	≥0,42	>0,40	>0,40		
	HSC - Stone Capital	R10	B	≥0,42	>0,40	>0,40		
	HSC - Stone Capital Grip	R12	C	≥0,42	>0,40	>0,40		
	HSF - Sassofeltro	R9		≥0,42	>0,40	>0,40		
	HSU - Soul	R10*	B*	≥0,42*	>0,40*	>0,40*		
	HTV - Tivoli	R9		≥0,42	>0,40	>0,40		
HUP - Upgrade	R10	B	≥0,42	>0,40	>0,40			
HEM - Elementi		B	≥0,42	>0,40	>0,40			
HEV - Evolution			≥0,42	>0,40				
Contract	HEV grip	R10	B	≥0,42				
	HEX - Experience		A	≥0,42				
	HFO - Forma	R9	A	≥0,42	>0,40	>0,40		
	HPV - Pienza	R11	B	≥0,42	>0,40	>0,40		
	HBP205	R11	C	≥0,42	>0,40	>0,40		
	HBP208	R11	C	≥0,42	>0,40	>0,40		
	HBQ2	R12	C	≥0,42	>0,40	>0,40		
	HCL2	R11	C	≥0,42	>0,40	>0,40		
	HDG2	R11	C	≥0,42	>0,40	>0,40		
	HDL2	R11	C	≥0,42	>0,40	>0,40		
Dae	HDV2	R11	C	≥0,42	>0,40	>0,40		
	HED2	R11	C	≥0,42	>0,40	>0,40		
	HEG2	R11	C	≥0,42	>0,40	>0,40		
	HEK2	R11	C	≥0,42	>0,40	>0,40		
	HMN2	R11	C	≥0,42	>0,40	>0,40		
	HNT2	R12	C	≥0,42	>0,40	>0,40		
	HPR2	R12	C	≥0,42	>0,40	>0,40		
	HRV2	R11	C	≥0,42	>0,40	>0,40		
	HSA2	R11	C	≥0,42	>0,40	>0,40		
	HSC2	R11	C	≥0,42	>0,40	>0,40		
	HSU2	R12	C	≥0,42	>0,40	>0,40		
	HTE2	R11	C	≥0,42	>0,40	>0,40		
	HUP2	R11	C	≥0,42	>0,40	>0,40		
	Super face	HPA Pandora	R10	B	≥0,42	>0,40	>0,40	
		OB Orto Botanico	R9	B	≥0,42	>0,40	>0,40	
Plus	EB							
	JS							
	MR							
	MV							
	PL							
	TR							