











TECHNICAL DATA

CENTURA

WALL AND FLOOR COVERINGS

MANUFACTURER	CAMPO
PRODUCT NAME	STARK – Carreaux de porcelaine

TESTED ITEMS		METHOD	REQUIRED STANDARD	RESULTS
Length and width		ISO 10545-2	± 0.5%	CONFORM
Thickness			± 5%	CONFORM
Orthogonality			± 0.6%	CONFORM
Water Absorption		ISO 10545-3	≤ 0.5%	CONFORM
Bending strength		ISO 10545-4	$R \geq 35 \text{ N/mm}^2$	CONFORM
Coefficient of linear thermal expansion between 20°C and 100°C		ISO 10545-8	$\leq 9 \times 10^{-6}$	$\leq 9 \times 10^{-6} \times \text{C}^{-1}$
Résistance aux chocs thermique		ISO 10545-11	—	RESIST
Breaking strength		ISO 10545-11	—	RESIST
Chemical resistance		ISO 10545-14	min. classe 3	CLASS 5
		ISO 10545-13	min. GB	CLASS GA/GLA
Flatness		ISO 10545-2	± 0.6%	CONFORM
Frost Resistance		ISO 10545-12	—	RESIST
Slip resistance		ASTM C1028/64	Water, oil, grease, etc. Create slippery conditions	DRY : 0.78 WET : 0.63
		DIN 51130 R		R9