

The Soul Collection  
**HEX CRAQUELE**

ø 31,75 mm (1,25")

■ **SUITABILITY AREA PRODUCT & COMPOSITION GUIDE**

REFERENCE	WALL	FLOOR	WET AREAS	POOLS	MATERIAL
All Products	Int/ Ext	Residential	Yes	Yes	Glass

■ **TECHNICAL CHARACTERISTICS**

TEST UNE-EN-ISO 10545-3 WATER ABSORPTION	TEST UNE-EN-ISO-101-92=101 SURFACE HARDNESS. MOSH.	TEST UNE-EN-ISO 10545-9 RESISTANCE TO THERMAL SHOCKS	TEST UNE-EN-ISO 10545-12 FROST RESISTANCE	TEST UNE-EN-ISO 10545-13:1998 RESISTANCE TO CHEMICAL ATTACK			
				DOMESTIC PRODUCTS	POOL WATER ADDITIVES	LOW ACID AND ALKALINS	HIGH ACID AND ALKALINS
None	4	Resistant	Resistant	GA	GA	GLA	GHA
TEST UNE-EN-ISO 10545-14 RESISTANCE TO STAINING	TEST UNE-EN-ISO 10545- 11=1997 CRACKING	DIN 51094 COLOUR STABILITY ON EXPOSURE TO LIGHT AND UV RAYS	DCOF WET DYNAMIC COEFFICIENT OF FRICTION ANSI A 137.1 STANDARD		DIN 51130:2004 SLIP RESISTANCE WEARING SHOES	DIN 51097 SLIP RESISTANCE IN BARE FEET	TEST UNE-ENV 12633:2003 (CTE) ANTI SKID COEFFICIENT, SUITABLE FOR OUTDOOR USE AND SWIMMING POOLS
Class 5	Resistant	Resistant	≥ 0,42*		R11*	Class C*	Class 3*

\*Matte products

■ **PACKING**

SHEET HOJA	BOX CAJA	PALLET PALET	EURO PALLET EURO PALET
Size / Dimensión: 301x290 mm (11.85"x11.41")	Sheets / Hojas: 6	Quantity / Cantidad: 90,63 m <sup>2</sup> (975.53 sqft)	Quantity / Cantidad: 80,56 m <sup>2</sup> (867.14 sqft)
Thickness / Espesor: 4,4 mm (0.173")	Quantity / Cantidad: 0,53 m <sup>2</sup> (5.71 sqft)	Boxes / Cajas: 171	Boxes / Cajas: 152
Weight / Peso: 0,87 Kg 1.92 lb	Weight / Peso: 5,22 kg (11.51 lb)	Gross weight / Peso bruto: 912,62 kg (2,011.4 lb)	Gross weight / Peso bruto: 826,44 Kg (1,821.5 lb)



Minimum  
Order  
1 module / 1 Box



Sales  
Unit  
Square meters



Mosaic  
Support  
MESH



Mosaic  
Support  
DOTS

All ONIX 98 % recycled glass mosaics series are made of molten glass. Molten glass characteristics may include irregular edges and small variations in size. These characteristics are inherent to the product and to the standard production. The small size and shape variations can affect the grout joint appearance and enhance the natural aspect of these products.