











4,30 mm / GLASS

Reference standard	Test method	Reference value	Declared value
 Amount of water absorbed, in percentage	ISO-10545-3	-	0 %
 Resistance to abrasion of glazed tiles	ISO-10545-7	-	5 (test on Extra Light - White)
 Coefficient of thermal linear expansion	ISO-10545-8	-	9,1 *10 ⁻⁶ °C ⁻¹
 Glaze crazing resistance	ISO-10545-11	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
 Resistance to high concentrations of acids and alkali	ISO-10545-13	-	GLA - ULA
 Resistance to low concentrations of acids and alkali	ISO-10545-13	-	GHA - UHA
 Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	-	GA - UA
 Resistance to staining	ISO-10545-14	-	5
 Colours resistance to fading	DIN-51094	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
 Barefoot slip resistance	DIN-51097	-	Cl. A + B + C