



CARACTÉRISTIQUES DE BASE:

| | |
|---------------------|--|
| Nom du matériau: | ARES WHITE POLISHED (PRC) 60X120RC/ARG_S |
| Format (cm): | 60x120 |
| Couleur: | WHITE |
| Numéro de la série: | ARES |
| Famille: | GRÈS CÉRAME GL |

CARACTÉRISTIQUES TECHNIQUES:

| | | |
|--|--------------------------------|--------------------|
| Procédé de fabrication: | Carreau céramique pressé à sec | |
| Groupe d'absorption(ISO 13006): | BIa | |
| Finition: | GL | |
| Rectifié: | Oui | |
| Type de pâte: | Pâte STD | |
| Format de fabrication (mm): | 600 x 1200 x 10,5 | |
| Classification esthétique et détonification: | V.3 | |
| Tolérances dimensionnelles et aspect de surface: | Conforme à la norme | UNE EN ISO 10545-2 |

PROPRIÉTÉS PHYSIQUES:

| | | |
|--|---------------------|--------------------|
| Absorption d'eau: | $E \leq 0.5$ | UNE EN ISO 10545-3 |
| Force de rupture (S): | $> 1300N$ | UNE EN ISO 10545-4 |
| Résistance à la flexion (N/mm ²): | $\geq 35 N/mm^2$ | |
| Dilatation thermique linéaire de 20° à 100° C: | Conforme à la norme | UNE EN ISO 10545-8 |

NOTES IMPORTANTES:

Before fixing tiles, please check the shade, calibre and choice. Claims regarding these items cannot be accepted once the materials has been fixed. Protecting the product during placement and appropriate cleaning after grouting and other work are part of a correct fitting process. For more information about the instalation and grouting visit the Argenta website: www.argentaceramica.com. The packing list of this pieces are indicated on the Argenta website: www.argentaceramica.com/packing-list. The stated weight is approximate, it may vary up to 5% depending on the model, the variation may begreater for products with relief.Document with commercial information and cannot be used either judicially or administratively without the express permission of Argenta Ceramica S.L.The color of the tile of this technical data is for guidance only and may differ from the actual tile color.

Certifications:





| | | |
|--|-----------------------|----------------------|
| Résistance aux chocs thermiques: | Conforme à la norme | UNE EN ISO 10545-9 |
| Résistance à la fissuration: | Conforme à la norme | UNE EN ISO 10545-11 |
| Dureté superficielle à la rayure (MOHS): | 4 | UNE EN 67-101-92 |
| Résistance au glissement: | Antidérapant Classe 0 | UNE - ENV 12633:2003 |

PROPRIÉTÉS CHIMIQUES:

| | | |
|---|---------------------|---------------------|
| Résistance aux produits chimiques et sels de piscine: | Conforme à la norme | UNE EN ISO 10545-13 |
| Résistance aux bases à forte concentration: | HA | |
| Résistance aux bases à faible concentration: | LA | |
| Résistance aux taches: | Classe 5 | UNE EN ISO 10545-14 |

MARQUAGE CE:

| | |
|--|---------------------|
| | 004CPR-PR/11-4-2013 |
|--|---------------------|

NOTES IMPORTANTES:

Before fixing tiles, please check the shade, calibre and choice. Claims regarding these items cannot be accepted once the materials has been fixed. Protecting the product during placement and appropriate cleaning after grouting and other work are part of a correct fitting process. For more information about the instalation and grouting visit the Argenta website: www.argentaceramica.com. The packing list of this pieces are indicated on the Argenta website: www.argentaceramica.com/packing-list. The stated weight is approximate, it may vary up to 5% depending on the model, the variation may begreater for products with relief.Document with commercial information and cannot be used either judicially or administratively without the express permission of Argenta Ceramica S.L.The color of the tile of this technical data is for guidance only and may differ from the actual tile color.

Certifications:

