

# Super Flex<sup>™</sup> Ultra-Premium Thin Set Mortar



## **1. PRODUCT NAME**

TEC<sup>®</sup> Super Flex<sup>™</sup> Ultra-Premium Thin Set Mortar (392/393)

## **2. MANUFACTURER**

H.B. Fuller Construction Products Inc. 1105 South Frontenac Street Aurora, IL 60504-6451 U.S.A. 800.552.6225 Office 800.952.2368 Fax tecspecialty.com

## **3. DESCRIPTION**

Whether for new construction or renovation, Super Flex<sup>™</sup> premium latex mortar delivers unsurpassed bonding strength with virtually any tile and substrate combination. Perfect for porcelain and most glass tile, Super Flex<sup>™</sup> mortar's high polymer solids content, together with its special adhesion promoter, ZS-100\*, give you unparalleled bond strength.

\* ZS-100 is covered under US patent number 5,366,550.

#### **Key Features and Benefits**

- Flexible: absorbs 1/16" (1.6 mm) in-plane movement
- Patented bonding formula
- Approved for up to 20" (50 cm) o.c. manufactured, I-beam, floor truss systems.
- · Best for bonding porcelain tile
- One part—just add water and mix
- Exceeds ANSI A118.4E, A118.11 and A118.15E specifications
- Interior/exterior use
- Zero VOC
- · Contains recycled materials\*
- \* Gray formula contains 7% pre-consumer recycled material. White formula contains 0% pre-consumer recycled material.

#### Packaging

50 lb. (22.68 kg) moisture-resistant bags Gray White	Product #3300383111 Product #3300393111
25 lb. (11.34 kg) moisture-resistant bags White	Product #3300393011
9.75 lb. Pure Pak* container (4.42 kg) White *Registered trademark of Excello Corporation	Product #3300395311

#### Coverage

Coverage will vary with condition of substrate. Required trowel size will vary with the tile size, type and substrate uniformity. Select the trowel size that will ensure 100% coverage. Figures below are presented only as guidelines.

	Approximate Coverage per		
Trowel Size	50 lbs.	25 lbs.	9.75 lbs.
	(22.68 kg)	(11.34 kg)	(4.42 kg)
<sup>3</sup> ⁄16" x <sup>5</sup> ⁄32" (4.7 x 4 mm) V-notch trowel	_	_	28-30 sq. ft. (2.6-2.8 m <sup>2</sup> )
1/4" x 1/4" x 1/4" (6 x 6 x 6 mm)	90-100 sq. ft.	45-50 sq. ft.	17-19 sq. ft.
square-notched trowel	(8.4-9.3 m²)	(4.2-4.6 m <sup>2</sup> )	(1.6-1.8 m <sup>2</sup> )
<sup>1</sup> /4" x <sup>3</sup> /8" x <sup>1</sup> /4" (6 x 9 x 6 mm)	65-75 sq. ft.	33-38 sq. ft.	12-14 sq. ft.
square-notch trowel	(6-7 m²)	(3.1-3.5 m²)	(1.1-1.3 m <sup>2</sup> )

#### **Suitable Substrates**

When properly prepared, suitable substrates include:

- Cured concrete, cured mortar beds, brick and masonry (interior and exterior installations)
- APA Grade Trademarked Exposure 1 Plywood [Underlayment grade or better, two layers,  $1\frac{1}{8}$ " (28 mm) total minimum thickness for joists 16" (40 cm) o.c., interior floors only].
- Gypsum wallboard (dry interior wall areas only)

- Water resistant gypsum wallboard (i.e.: greenboard, interior walls only, dry to intermittent water exposure only)
- Cementitious backer units (CBU) or glass mat backerboard
- Existing ceramic tile and natural stone, provided existing flooring is well-bonded to an approved substrate.
- Vinyl composition tile, asphalt tile, linoleum or non-cushioned vinyl sheetgoods provided such surfaces are single layered, well-bonded to an approved substrate and properly prepared.
- Plastic laminate (interior countertops only) provided the counter is structurally sound and level.
- · Adhesive residue (except tacky or pressure-sensitive adhesive).

#### **Substrate Preparation**

All substrates must be dry, structurally sound with maximum deflection per industry standards of  $V_{360}$  for ceramic tile installations and  $V_{720}$  for natural stone installations; and free from oil, grease, dust, paint, sealers or concrete curing compounds. All contaminants must be removed prior to installation of tile. Surface protrusions and tile glazes shall be removed by sanding, scraping or scarifying. After preparation, remove all dust by vacuuming.

Notes: Vinyl asbestos tile or any substrate containing asbestos must not be sanded, scored or scarified because of the potential health hazard of breathing dust. Any substrate containing asbestos must be handled in accordance with existing EPA regulations. Contact your local EPA office.

Expansion joints must be provided in the tile work over all construction, control and expansion joints in the backing and where backing materials change. Follow ANSI A108.01 Section 3.7 Requirements for Expansion Joints.

Maximum variations in all substrates must not exceed  $\frac{1}{4}$ " in 10 ft. (6 mm in 3 m) or  $\frac{1}{16}$ " in 1 ft. (1.6 mm in 0.3 m) from the required plane. For non-level, interior surfaces use TEC<sup>®</sup> EZ Level<sup>®</sup> Premium Self Leveling Underlayment.

#### Storage

Store in a cool, dry area away from direct sunlight. Do not store open containers.

### Shelf Life

Maximum of 1 year from date of manufacture in unopened package.

#### Limitations

- Glass tile may not be suitable over some substrates (such as plywood, or some membranes). Verify substrate with the glass tile manufacturer.
- Use only for thin-bed installation of glass tile.
- Contact TEC<sup>®</sup> Technical support before installing glass with a decorative coating on the tile backing or glass tile larger than 6" x 6" (15 x 15 cm) as these materials require more detailed precautions.
- Not for installing green marble, other moisture-sensitive stone tile or resinbacked marble; use TEC<sup>®</sup> AccuColor EFX<sup>®</sup> Epoxy Grout and Mortar.
- For non-green marble tile applications, use white thin set mortars.
- Not for use over rubber, strip wood floors, oriented strand board, particle board, lauan plywood.
- Do not apply over single layer wood floors.
- Mortar should not be applied when the temperature of the area and substrate to be tiled is below 50°F (10°C) as this delays the curing process.
- Certain natural stone tiles may be affected by mortar shadowing or staining. Test a small area prior to use to determine suitability.

#### Cautions

Read complete cautionary information printed on product container prior to use. For medical emergency information, call 1-888-853-1758.

This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about and guidelines for the proper use and application of the covered TEC<sup>®</sup> brand product(s) under normal environmental and working conditions. Because each project is different, H.B. Fuller Construction Products Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

## TEC<sup>®</sup> Super Flex<sup>™</sup> Ultra-Premium Thin Set Mortar \_

## **4. TECHNICAL DATA**

#### **Applicable Standard**

Exceeds ANSI A118.4E, A118.11 and A118.15E specifications ISO 13007: Classification C2ES1P2

Super Flex™ Ultra-Premium Thin Set Mortar (392/393)			
Description	ANSI Requirement	Typical Results	
28 Day Shear Strength Glazed Wall Tile Impervious Ceramic Tile (Porcelain) Quarry Tile	> 450 psi (3.10 MPa) > 400 psi (2.76 MPa) > 150 psi (1.03 MPa)	> 600 psi* (4.1 MPa) 700 psi (4.8 MPa) 725 psi (5.0 MPa) * ANSI-specified glazed wall tile failed at 600 psi (4.1 MPa)	
Sag on Vertical Surfaces	≤ <sup>1</sup> ∕16" (1.6 mm)	0-1/32" (0-0.8 mm)	
Extended Open Time	> 75 psi (0.5 MPa) at 30 Minutes	Pass	
Adjustability at Room Temperature	≥ 30 minutes	50-70 minutes	
Final Set	9-15 hours	11-13 hours	
Tested in accordance with ANSI A118.15E Specific	cations for Latex-Modified Dry Set N	Nortars	
Flexibility (movement absorbed before shear) Porcelain to Concrete	No ANSI spec currently available	<sup>1</sup> ⁄16" (1.6 mm)	
Tested in accordance with ANSI A118.11 Specifica	tions for Latex-Modified Dry Set M	ortars over Exterior Grade Plywood	
28 Day Shear Strength Quarry Tile	> 150 psi (1.0 MPa)	335 psi** (2.3 MPa) ** Plywood laminates typically failed over 325 psi (2.2 MPa)	

 $\label{eq:Greater than:} {\sf Greater than or equal to:} \geq {\sf Less than:} {\sf < Less than or equal to:} \leq$ 

#### **Physical Properties**

Description	
Physical State	Dry powder
Color	Available in white and gray
Pot Life	2 to 3 hours
Initial Cure [at 72°F (22°C)	16 to 24 hours
Final Cure	21 days
Foot Traffic Rating (ASTM C627)	Residential to Extra Heavy Commercial (depending on substrate)
Storage	Store in a cool, dry area away from direct sunlight. Do not store open containers.
Shelf Life	Maximum 1 year from date of manufacture in properly stored, unopened package.

## **5. INSTALLATION INSTRUCTIONS**

#### Mixing

For best results, maintain all tiling materials, substrates, room and adhesives at 50°-70°F (10-21°C) for 24 hours before installation. Maintain recommended room temperature for 48 hours after installation. In a clean mixing container, add Super Flex<sup>™</sup> mortar to clean, cool water as specified in the chart.

41/2 to 6 quarts (4.3-5.7 L)
21/2 to 3 quarts (2.3-2.8 L)
28-37 fl. oz. (0.83-1.09 L)

Add powder to liquid for ease of mixing. Mix material to a thick creamy consistency. Avoid breathing dust and contact with eyes and skin. Allow the mortar to stand for 10 minutes. Remix and apply. Avoid using high speed mixing, not to exceed 300 rpm, to prevent entraining air.

#### Application

Apply mortar using flat side of trowel to promote better substrate contact, then comb in one direction with the notched side of the trowel. Spread only an area that can be tiled while surface is still tacky (typically 20-30 minutes). Press tiles into setting bed, then push in a direction perpendicular to the notched trowel ridges to achieve optimum coverage. Apply mortar in a heavy enough layer so that complete contact (no voids) between mortar and tile is accomplished when tile is positioned. It may be necessary to "back-butter" large tiles to achieve complete coverage and firm support. Periodically remove and check a tile to assure proper coverage. Keep a minimum of  $\frac{2}{3}$  of the joint depth between tiles for grouting.

Open time and tile hand adjustability may vary with job site conditions. Stir occasionally during use to maintain the smooth, creamy consistency of the product. **Do not add additional water.** 

#### Clean-up

Clean tools, hands, and excess materials from face of tile, while mortar is still fresh, with warm soapy water.

#### **Grouting/Curing**

Grouting may be accomplished when tiles are held firmly in place, typically 16 to 24 hours after installation is completed. No traffic is permitted over the tiles prior to grouting. Cold temperatures or high humidity may extend curing time. Unglazed tiles may require sealing prior to grouting so discolorations will not occur. The use of TEC<sup>®</sup> brand grouts is highly recommended.

## 6. AVAILABILITY

TEC<sup>®</sup> Premium Tile and Stone Installation Products are available nationwide. To locate TEC<sup>®</sup> products in your area, please contact: Phone: 800-832-9002 Website: tecspecialty.com

## 7. WARRANTY

For warranty details, see your sales associate or visit tecspecialty.com.

#### 8. MAINTENANCE

Not applicable

## 9. TECHNICAL SERVICES

#### **Technical assistance**

Information is available by calling the Technical Support Hotline. Toll Free: 800-832-9023 Fax: 630-952-1235

#### Technical and safety literature

To acquire technical and safety literature, please visit our website at tecspecialty.com.

#### **10. FILING SYSTEM**

Division 9



#### tecspecialty.com

©Copyright 2017 H.B. Fuller Construction Products Inc. TEC<sup>®</sup>, TEC<sup>®</sup> logo, Super Flex<sup>™</sup>, EZ Level<sup>®</sup> and AccuColor EFX<sup>®</sup> are trademarks of H.B. Fuller Construction Products Inc.

